

## 試驗報告

號碼：KE/2018/12658A-01

日期：2018/2/5

頁數：1 of 6

台灣塑膠工業股份有限公司  
高雄市林園區石化一路1號

以下測試樣品係由客戶送樣，且由客戶聲稱並經客戶確認如下：

樣品名稱	:	嵌段耐衝擊共聚物聚丙烯
樣品型號	:	3003,3003H,3004,3005,3005H,3010,3015,3020,3040,3040C, 3064H,3080,3084,3084H,3090,3155,3200W,3204,3354,3504, 4084,4204,4304,4604,6025.
樣品材質	:	嵌段耐衝擊共聚物聚丙烯
樣品顏色	:	白色微透明
收件日期	:	2018/01/30.
測試期間	:	2018/01/30 TO 2018/2/5
送樣廠商	:	台灣塑膠工業股份有限公司

=====  
測試結果 : 請見下一頁.

張伯睿  
報告簽署人/張伯睿 博士/技術經理



# 試驗報告

號碼：KE/2018/12658A-01

日期：2018/2/5

頁數：2 of 6

台灣塑膠工業股份有限公司  
 高雄市林園區石化一路1號

## 測試結果

測試部位 NO.1 : 白色微透明嵌段耐衝擊共聚物聚丙烯

測試項目	單位	測試方法	方法偵測	結果
			極限值	NO.1
鄰苯二甲酸單丁酯 (MBP) (CAS No.: 131-70-4)	%	本測試參考EN 14372, 以氣相層析儀/質譜儀檢測之。	0.003	n.d.
鄰苯二甲酸二(2-丙基庚)酯 (DPrHP) (CAS No.: 53306-54-0)	%		0.003	n.d.
支鏈和直鏈1,2-鄰苯二甲酸二己酯 (CAS No.: 68515-50-4)	%		0.01	n.d.
支鏈和直鏈1,2-苯二羧二戊酯 (CAS No.: 84777-06-0)	%		0.003	n.d.
鄰苯二甲酸正戊基異戊基酯 (nPiPP) (CAS No.: 776297-69-9)	%		0.003	n.d.
己二酸二異壬酯 (DINA) (CAS No.: 33703-08-1)	%		0.01	n.d.
鄰苯二甲酸丁苯甲酯 (BBP) (CAS No.: 85-68-7)	%		0.003	n.d.
鄰苯二甲酸二丁酯 (DBP) (CAS No.: 84-74-2)	%		0.003	n.d.
鄰苯二甲酸二(2-乙基己基)酯 (DEHP) (CAS No.: 117-81-7)	%		0.003	n.d.
鄰苯二甲酸二異癸酯 (DIDP) (CAS No.: 26761-40-0, 68515-49-1)	%		0.01	n.d.
鄰苯二甲酸二異壬酯 (DINP) (CAS No.: 28553-12-0, 68515-48-0)	%		0.01	n.d.
鄰苯二甲酸二正辛酯 (DNOP) (CAS No.: 117-84-0)	%		0.003	n.d.
己二酸二(2-乙基己基)酯 (DEHA) (CAS No.: 103-23-1)	%		0.003	n.d.
鄰苯二甲酸二異丁酯 (DIBP) (CAS No.: 84-69-5)	%		0.003	n.d.
鄰苯二甲酸二甲酯 (DMP) (CAS No.: 131-11-3)	%		0.003	n.d.
鄰苯二甲酸二丙酯 (DPrP) (CAS No.: 131-16-8)	%	0.003	n.d.	

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部分複製。  
 This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

# 試驗報告

號碼：KE/2018/12658A-01

日期：2018/2/5

頁數：3 of 6

 台灣塑膠工業股份有限公司  
 高雄市林園區石化一路1號

測試項目	單位	測試方法	方法偵測	結果
			極限值	NO.1
鄰苯二甲酸二環己酯 (DCHP) (CAS No.: 84-61-7)	%	本測試參考EN 14372, 以氣相層析儀/質譜儀檢測之。	0.003	n.d.
鄰苯二甲酸二乙酯 (DEP) (CAS No.: 84-66-2)	%		0.003	n.d.
鄰苯二甲二異辛酯 (DIOP) (CAS No.: 27554-26-3)	%		0.01	n.d.
鄰苯二甲酸二正壬酯 (DNNP) (CAS No.: 84-76-4)	%		0.003	n.d.
鄰苯二甲酸二己酯 (DNHP) (CAS No.: 84-75-3)	%		0.003	n.d.
鄰苯二甲酸二(2-甲氧基乙基)酯 (DMEP) (CAS No.: 117-82-8)	%		0.003	n.d.
鄰苯二甲酸二苯甲基酯 (DBZP) (CAS No.: 523-31-9)	%		0.003	n.d.
鄰苯二甲酸二苯基酯 (DPhP) (CAS No.: 84-62-8)	%		0.003	n.d.
鄰苯二甲酸二異戊酯 (DIPP) (CAS No.: 605-50-5)	%		0.003	n.d.
鄰苯二甲酸二(2-乙氧基乙基)酯 (DEEP) (CAS No.: 605-54-9)	%		0.003	n.d.
鄰苯二甲酸二(C6-8支鏈與直鏈)烷基酯, 富C7 (DIHP) (CAS No.: 71888-89-6)	%		0.01	n.d.
鄰苯二甲酸二(C7-11支鏈與直鏈)烷基酯 (DHNUP) (CAS No.: 68515-42-4)	%		0.01	n.d.
鄰苯二甲酸二烯丙酯 (DAP) (CAS No.: 131-17-9)	%		0.003	n.d.
鄰苯二甲酸二正戊酯 (DNPP) (CAS No.: 131-18-0)	%		0.003	n.d.
鄰苯二甲酸-單-乙基己基酯 (MEHP) (CAS No.: 4376-20-9)	%		0.003	n.d.
對苯二甲酸(2-乙基己)酯 (DEHT) (CAS No.: 6422-86-2)	%		0.003	n.d.
鄰苯二甲酸雙十一烷基酯 (DUDP) (CAS No.: 3648-20-2)	%		0.01	n.d.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部分複製。  
 This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

# 試驗報告

號碼：KE/2018/12658A-01

日期：2018/2/5

頁數：4 of 6

 台灣塑膠工業股份有限公司  
 高雄市林園區石化一路1號

測試項目	單位	測試方法	方法偵測 極限值	結果
				NO.1
對苯二甲酸二甲酯 (DMTP) (CAS No.: 120-61-6)	%	本測試參考EN 14372, 以氣相層析儀/質譜儀檢測之。	0.003	n.d.
鄰苯二甲酸二癸酯 (DNDP) (CAS No.: 87-77-5)	%		0.003	n.d.
鄰苯二甲酸二(2-丁氧基)乙酯 (DBEP) (CAS No.: 117-83-9)	%		0.003	n.d.
鄰苯二甲酸二(4-甲基-2-戊基)酯 (BMPP) (CAS No.: 146-50-9)	%		0.003	n.d.
鄰苯二甲酸二庚酯 (DHPP) (CAS No.: 3648-21-3)	%		0.003	n.d.
1,2-苯二甲酸,二(C6-10)烷基酯; 1,2-苯二甲酸, 混合二己二辛二癸酯, 其中鄰苯二甲酸二己酯 (EC號201-559-5) 必須 ≥ 0.3% (CAS No.: 68515-51-5/68648-93-1)	%		0.01	n.d.
鄰苯二甲酸二異己酯(DIHxP) (CAS No.: 71850-09-4)	%		0.01	n.d.
1,2-苯二甲酸,二(C6-10)烷基酯; 1,2-苯二甲酸, 混合二己二辛二癸酯, 其中鄰苯二甲酸二己酯 (EC號201-559-5) 必須 ≥ 0.3% (CAS No.: 68515-51-5/68648-93-1)	%		0.01	n.d.

- 備註： 1. mg/kg = ppm ; 0.1wt% = 1000ppm  
 2. n.d. = Not Detected / 未檢出  
 3. MDL = Method Detection Limit / 方法偵測極限值  
 4. 此為2018/02/05所發行KE/2018/12658之加發報告，原始資料請參考KE/2018/12658。

## 試驗報告

號碼：KE/2018/12658A-01

日期：2018/2/5


頁數：5 of 6

台灣塑膠工業股份有限公司  
 高雄市林園區石化一路1號

### 可塑劑分析流程圖

1)測試人員：陳威錚

2)測試負責人：張伯睿



## 試驗報告

號碼：KE/2018/12658A-01

日期：2018/2/5

頁數：6 of 6

台灣塑膠工業股份有限公司  
高雄市林園區石化一路1號

\* 照片中如有箭頭標示，則表示為實際檢測之樣品/部位。 \*

# KE/2018/12658



\*\* 報告結尾 \*\*

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部分複製。  
This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.