

永嘉烯 YUNGSOX

1030T

均聚物 HOMOPOLYMER

用途 Applications

- 透明壓空成型板
Transparency pressure forming sheet
- 文件夾 Portfolio

特性 Characteristics

- 超高透明性佳 Excellent transparency
- 高剛性 High stiffness
- 高耐熱性 High heat resistance

物性 Typical Properties

項目 Properties	單位 Unit	檢驗方法 Test Method	平均值 Typical Value
熔融指數 Melt Index	g/10min	ISO1133 (ASTM D-1238)	3.0
密度 Density	g/cm ³	ISO1183 (ASTM D792)	0.91
熔點 Melting Point	°C	DSC	---
熱變形溫度 Heat Deflection Temperature	°C	ISO75 (ASTM D-648)	105
軟化點溫度 Vicat Softening Temperature	°C	ISO306	150
降伏點拉力強度 Tensile Strength at Yield	Kg/cm ² (MPa)	ISO527 (ASTM D-638)	350 (34)
斷裂點伸長率 Tensile Elongation at Break	%	ISO527 (ASTM D-638)	400
洛氏硬度 Rockwell Hardness	R scale	ISO2039 (ASTM D-785)	105
剛性係數 Flexural Modulus	Kg/cm ² (MPa)	ISO178 (ASTM D-790)	14,000 (1373)
IZOD 衝擊強度 IZOD Impact Strength	Kg.cm/cm Notch (J/m)	ISO 180 (ASTM D-256)	23°C 8 (78) -20°C ---
收縮率 Mold Shrinkage	%	FPC Method	1.3-1.7

本表數據為代表值，僅供選擇品級用途之參考

The details given in this data sheet are our standard value but not specification guaranteed.

FDA 認可 FDA Approval

永嘉烯 1030T 符合美國食品及藥物管理局 21 CFR 177.1520 之規範，可直接與食物接觸。

Yungsox 1030T resin meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.

JHOSPA-PL 認證 JHOSPA-PL Certification

永嘉烯 1030T 通過日本 JHOSPA-PL 認證。

Yungsox 1030T resin meets the requirements of JHOSPA-PL Certification.

Oct 2023