

永嘉烯 YUNGSOX

2020S

均聚物 HOMOPOLYMER

用途 Applications

- BOPP 膜 BOPP film
- 高級食品、服裝及飾品包裝
High quality food, garment and garnish packaging
- 透明膠帶及裝飾紙積層膜 Tape

特性 Characteristics

- 高速生產性優
Excellent processing for high speed
- 透明性優 Excellent transparency
- 光澤性佳 Good luster

物性 Typical Properties

項目 Properties	單位 Unit	檢驗方法 Test Method	平均值 Typical Value
熔融指數 Melt Index	g/10min	ISO1133 (ASTM D-1238)	3
密度 Density	g/cm ³	ISO1183 (ASTM D792)	0.90
熔點 Melting Point	°C	DSC	160
熱變形溫度 Heat Deflection Temperature	°C	ISO75 (ASTM D-648)	113
軟化點溫度 Vicat Softening Temperature	°C	ISO306	150
降伏點拉力強度 Tensile Strength at Yield	Kg/cm ² (MPa)	ISO527 (ASTM D-638)	350 (34)
斷裂點伸長率 Tensile Elongation at Break	%	ISO527 (ASTM D-638)	600
洛氏硬度 Rockwell Hardness	R scale	ISO2039 (ASTM D-785)	105
剛性係數 Flexural Modulus	Kg/cm ² (MPa)	ISO178 (ASTM D-790)	12,500 (1226)
IZOD 衝擊強度 IZOD Impact Strength	Kg.cm/cm Notch (J/m)	ISO 180 (ASTM D-256)	23°C 4.5 (44) -20°C ---
收縮率 Mold Shrinkage	%	FPC Method	1.3-1.7
濁度 Haze (30μ)	%	FPC Method	< 0.11

本表數據為代表值，僅供選擇品級用途之參考

The details given in this data sheet are our standard value but not specification guaranteed.

FDA 認可 FDA Approval

永嘉烯 2020S 符合美國食品及藥物管理局 21 CFR 177.1520 之規範，可直接與食物接觸。

Yungsox 2020S resin meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.

JHOSPA-PL 認證 JHOSPA-PL Certification

永嘉烯 2020S 通過日本 JHOSPA-PL 認證。

Yungsox 2020S resin meets the requirements of JHOSPA-PL Certification.

